

Product Information Bulletin

BULLETIN NO.	212	
ISSUED:	December 19, 2019	
REPLACES:	December 10, 2019	

PlastiSpan® HD Insulation - CAN/ULC-S701.1, Type 2 Material Properties

PlastiSpan® HD insulation is a rigid, closed-cell expanded polystyrene (EPS) insulation that meets or exceeds material property requirements for CAN/ULC-S701.1 (formerly CAN/ULC-S701), Type 2. The table below provides material properties for **PlastiSpan HD** insulation.

Material Properties ¹	Units	Values
Thermal Resistance	m ² •°C/W	0.70
Minimum per 25 mm (1 inch) ASTM C518	(ft²•h•°F/BTU)	(4.04)
Compressive Resistance	kPa	110
Minimum @ 10% Strain ASTM D1621	(psi)	(16)
Flexural Strength	kPa	240
Minimum ASTM C203	(psi)	(35)
Water Vapour Permeance ²	ng/(Pa•s•m²)	200
Maximum ASTM E96	(Perms)	(3.5)
Water Absorption ³ Maximum ASTM D2842	% By Volume	4.0
Dimensional Stability Maximum ASTM D2126	% Linear Change	1.5
Limiting Oxygen Index Minimum ASTM D2863	% Volume	24
Flame Spread Rating CAN/ULC S102.2	NA	290
Smoke Developed Classification CAN/ULC S102.2	NA	Over 500

Sustainability

As part of its commitment to ongoing sustainability initiatives, Plasti-Fab maintains *GREENGUARD Gold Certification* for *PlastiSpan HD* insulation with UL Environment, an independent global safety science organization. The *GREENGUARD Gold Certification* mark on *PlastiSpan HD* insulation gives assurance that insulation designed for use in indoor spaces meets strict chemical emissions limits, which contribute to the creation of healthier interiors (see Plasti-Fab PIB 266 for additional information).

^{1.} *PlastiSpan HD* insulation properties are third party certified to CAN/ULC-S701.1, *Standard for Thermal Insulation, Polystyrene Boards*, under an Intertek third party certification program (see Intertek Code Compliance Research Report CCRR-1072 for additional information) and is listed by the Canadian Construction Materials Centre (CCMC) under evaluation listing number 12425-L (Type 2).

^{2.} WVP values quoted are maximum values for 25-mm (1-inch) thick samples with natural skins intact. Lower values will result for thicker materials.

^{3.} The water absorption laboratory test method involves complete submersion under a head of water for 96 hours. The water absorption values above are applicable to specific end-use design requirements only to the extent that the end-use conditions are similar to test method requirements.