

## **Product Information Bulletin**

BULLETIN NO.	213
ISSUED:	December 19, 2019
REPLACES:	December 10, 2019

## PlastiSpan® 25 Insulation - CAN/ULC-S701.1, Type 3 Material Properties

**PlastiSpan® 25** insulation is a rigid, closed-cell expanded polystyrene (EPS) insulation that meets or exceeds material property requirements for CAN/ULC-S701.1 (formerly CAN/ULC-S701), Type 3. The table below provides material properties for **PlastiSpan 25** insulation.

Material Properties <sup>1</sup>	Units	Values
Thermal Resistance	m <sup>2</sup> •°C/W	0.74
Minimum per 25 mm (1 inch) ASTM C518	(ft²•h•°F/BTU)	(4.27)
Compressive Resistance	kPa	170
Minimum @ 10% Strain ASTM D1621	(psi)	(25)
Flexural Strength	kPa	300
Minimum ASTM C203	(psi)	(44)
Water Vapour Permeance <sup>2</sup>	ng/(Pa·s·m²)	130
Maximum ASTM E96	(Perms)	(2.25)
Water Absorption <sup>3</sup>	0/ 5	2.0
Maximum ASTM D2842	% By volume	
Dimensional Stability  Maximum  ASTM D2126	% Linear Change	1.5
Limiting Oxygen Index Minimum ASTM D2863	%	24
Flame Spread Rating CAN/ULC S102.2	NA	290
Smoke Developed Classification CAN/ULC S102.2	NA	Over 500

## Sustainability

As part of its commitment to ongoing sustainability initiatives, Plasti-Fab maintains *GREENGUARD Gold Certification* for *PlastiSpan 25* insulation with UL Environment, an independent global safety science organization. The *GREENGUARD Gold Certification* mark on *PlastiSpan 25* insulation gives assurance that insulation designed for use in indoor spaces meets strict chemical emissions limits, which contribute to the creation of healthier interiors (see Plasti-Fab PIB 266 for additional information).

<sup>&</sup>lt;sup>1.</sup> PlastiSpan 25 insulation properties are third party certified to CAN/ULC-S701.1, Standard for Thermal Insulation, Polystyrene Boards, under an Intertek third party certification program (see Intertek Code Compliance Research Report CCRR-1072 for additional information) and is listed by the Canadian Construction Materials Centre (CCMC) under evaluation listing number 12426-L (Type 3).
<sup>2.</sup> WVP values quoted are maximum values for 25-mm (1-inch) thick samples with natural skins intact.

Ewer values quoted are maximum values for 25-mm (1-inch) thick samples with natural skins intact. Lower values will result for thicker materials.

<sup>&</sup>lt;sup>3.</sup> The water absorption laboratory test method involves complete submersion under a head of water for 96 hours. The water absorption values above are applicable to specific end-use design requirements only to the extent that the end-use conditions are similar to test method requirements.